

## Metallic Salt

### Technical Data

Chemical name	Dibasic lead phosphite	Tribasic lead sulphate
Formula	$2\text{PbO}\cdot\text{PbHPO}_3\cdot 1/2\text{H}_2\text{O}$	$3\text{PbO}\cdot\text{PbSO}_4\cdot\text{H}_2\text{O}$
NJC code	Stabilizer D	Stabilizer T
Pbo content	85.6-88.8%	88.0-90.0%
Ash (%)	97.9-99.9	96.0-98.0
Moisture content	Max.0.4	Max.0.4
Sieve residue(%) 0.075mm-mesh	Max.0.2	Max.0.2
Density (g/cm)	7.0	6.6

### Description

As single or one pack heat stabilizer, DBLP/TBLS are widely used in the processing of rigid PVC products such as window profile, pipe & fittings, board & sheet etc. With the modern plant and management, our products are endowed such properties as the fire resistance, good dispersion with excellent heat and light stability. Meanwhile, the consistency of the products is maintained with the strict ISO quality management system.

### Package and Storage

25kg/1000kg paper/PE bags or according to customer's requirement.

Stored in cool and dry spaces. Period of quality guarantee is one year.

NANJING JINLING CHEMICAL CO.,LTD.

Add:No.55, NJC Road, Chemical Industry Park Nanjing China.

Tel: (025) 85315451、84712677、84716016

Email: angel.cai@njchem.net

Post Code: 210047

Fax: (025) 85315451

Web: www.njchem.net